

On page 7 of the specification after line 17, please insert and center the following:

A2 --Brief Description of the Drawings--

After "Brief Description of the Drawings" please insert the following:

A3 --FIG 1 shows aerogel particles; and
FIG 2 shows a view of NaCl crystals in an aerogel monolith using a scanning electron microscope.--

Support for the descriptions of the figures may be found throughout the specification specifically, for example, on page 26, lines 14-26 of the specification.

IN THE CLAIMS

Please amend claims as follows:

A4 Claim 3. (Amended) Method for the production of organically modified aerogels, characterized in that:

- SUB
B3
- a) a silicatic hydrogel is formed at $\text{pH} \geq 3$;
 - b) the silicatic hydrogel formed in step a) (optionally after intermediate treatment steps) is subjected to surface modification by mixing the hydrogel with hydrophobing agent to form a surface modified gel;
 - c) the surface modified gel obtained in step b) (optionally after additional treatment steps) is dried,

wherein the silicatic hydrogel is prepared by bringing an aqueous waterglass solution to a pH ≤ 3 with the aid of an acidic ion exchanger resin, a mineral acid, polycondensing the resulting silicic acid by addition of a base to form an SiO_2 gel, and, if desired, washing the gel with water to free it from any electrolyte.

Claim 5. (Amended) Method for the production of organically modified aerogels, characterized in that:

- a) a silicatic hydrogel is formed at $\text{pH} \geq 3$;
 - b) the silicatic hydrogel formed in step a), optionally after intermediate treatment steps, is subjected to surface modification by mixing the hydrogel with hydrophobing agent to form a surface modified gel;
 - c) the surface modified gel obtained in step b), optionally after additional treatment steps, is dried,
- wherein the silicatic hydrogel is obtained by hydrolysis and polycondensation of silicon tetrachloride.

Claim 6. (Amended) The process as claimed in claim 2, wherein additives are added before and/or during the preparation of the gel.

Claim 8. (Amended) The process according to claim 1, wherein the hydrogel obtained in step a) is aged before being surface-modified in step b).

Claim 9. (Amended) The process according to claim 1, wherein the hydrogel obtained in step b) is subjected to surface silylation using a silylating agent.

Claim 16. (Amended) The process as claimed in claim 13, wherein the silylating agent employed is hexamethyldisiloxane.

A7
cont. Claim 17. (Amended) The process as claimed in claim 1, wherein at least one acid and/or base is introduced as initial charge in the hydrogel before surface modification.

A8 Claim 19. (Amended) The process as claimed in claim 9, wherein the hydrogel is introduced as initial charge in the silylating agent, and then at least one acid and/or base is added. *Indon Feb 23rd*

A9
SUB
103
Claim 22. (Amended) The process as claimed in claim 1, wherein the agent for surface modification is generated shortly before and/or during the surface modification, (preferably by means of an acid.)

Claim 23. (Amended) The process as claimed in claim 1, wherein the surface modification is accelerated by means of a catalyst.

Claim 24. (Amended) The process as claimed in claim 1, wherein at least one carrier gas or carrier gas stream is used in step b) in addition to the agent for surface modification.

Claim 25. (Amended) The process as claimed in claim 1, wherein some of the water in pores of the hydrogel reacts with the surface modification agent to form a water-insoluble compound. *eg to form HMDSO*

A10 Claim 27. (Amended) The process as claimed in claim 1, wherein an outer surface of the hydrogel is dried prior to surface modification.

A11 Claim 31. (Amended) The process as claimed in claim 1, wherein the surface-modified gel is washed with a protic or aprotic solvent prior to step c). *surface modified*

A11
cont.
Claim 32. (Amended) The process as claimed in claim 1, wherein the surface-modified gel is washed with a silylating agent prior to step c).

Claim 33. (Amended) The process as claimed in claim 1, wherein the surface-modified gel is subjected to subcritical drying in step c).

SUB
B7/
Claim 34. (Amended) The process as claimed in claim 2, wherein the gel obtained in step a) is reacted, prior to silylation, with a solution of a condensable orthosilicate of the formula $R^{1}_{4-n}Si(OR^2)_n$, preferably an alkyl and/or aryl orthosilicate, where $n = 2$ to 4 and R^1 and R^2 independently of one another are hydrogen atoms or linear or branched C_1 - C_6 alkyl, cyclohexyl or phenyl radical, or with an aqueous silicic acid solution.

Claim 35. (Amended) The process as claimed in claim 1, wherein surface modification is carried out in the presence of additives in the hydrogel.

A12
112, 113, 114
Claim 39. (Amended) An aerogel whose internal surface is covered by at least 90% of the theoretically possible value with organic surface groups which have been applied by surface modification.

A13
Claim 42. (Amended) An aerogel as claimed in claim 41, which comprises ionic compounds as additives.

Claim 43. (Amended) The aerogel as claimed in claim 41, which comprises opacifiers as additives.

Claim 44. (Amended) The aerogel as claimed in claim 41 which comprises fibers as additives.

eg glass, mineral
ceramic, nylon

A13
cont

Claim 45. (Amended) The aerogel as claimed in claim 41, which has a BET internal surface area of less than $600 \text{ m}^2/\text{g}$.

Claim 46. (Amended) The aerogel as claimed in claim 41, which has a thermal conductivity of $< 12 \text{ mW/mK}$.

112
112

Claim 47. (Amended) The aerogel as claimed in claim 38, which is based on silicate.

112
112

Claim 48. (Amended) The use of an aerogel as claimed in claim 38 as a thermal insulation material.

A14
112, 115

Claim 51. (Amended) A lyogel whose internal surface is covered, by at least 90% of the theoretically possible value, with organic surface groups which have been applied by surface modification.

A15
112, 115

Claim 53. (Amended) The use of a lyogel as claimed in claim 50 (or 51 in chromatography, in cosmetology and in the pharmaceuticals sector.

Please add following new claims 54-66:

A16
SUB
B107

--54. (NEW) Method for the production of organically modified aerogels, characterized in that:

- a) a hydrogel is formed at $\text{pH} \geq 3$;
- b) the hydrogel formed in step a), optionally after intermediate treatment steps, is subjected to surface modification by mixing the hydrogel with hydrophobing agent to form a surface modified gel;

Preliminary Amendment

Page 6

A 16
cont.

c) the surface modified gel obtained in step b), optionally after additional treatment steps, is dried. --

--55. (NEW) The method for the production of organically modified aerogel according to claim 54, characterized in that the hydrogel is formed in step a) at pH between pH 3 and pH 8.--

--56. (NEW) The method for the production of organically modified aerogel according to claim 54 or 55, characterized in that the hydrogel is formed in step a) by lowering the pH of an aqueous waterglass solution.--

SUB
B10

--57. (NEW) The method for the production of organically modified aerogel according to claim 55, characterized in that the pH of an aqueous waterglass solution is lowered in step a) to a pH value not less than 3. --

--58. (NEW) Method for the production of organically modified aerogels/characterized in that a) a hydrogel is formed by lowering the pH of an aqueous waterglass solution by addition of acid to $\text{pH} \geq 8$ and establishing the pH between pH 3 and pH 8; b) the hydrogel formed in step a) optionally after intermediate treatment steps, is subjected to surface modification by mixing the hydrogel with hydrophobing agent to form a surface modified gel; and c) the surface modified gel obtained in step b), optionally after additional treatment steps, is dried.--

--59. (NEW) The method for the production of organically modified aerogel according to claim 54 or 55, characterized in that the hydrogel is formed in step a) by addition of acid to aqueous waterglass solution and without subsequent addition of base in step a).--

Alto
cont.

--60. (NEW) The method for the production of organically modified aerogel according to claim 54 or 55, characterized in that step a) and b) are carried out as a semi-continuous process.--

--61. (NEW) The method for the production of organically modified aerogel according to claim 54 or 55, characterized in that steps a) and b) are carried out as a continuous process.--

--62. (NEW) The method for the production of organically modified aerogel according to claim 60 or 61, characterized in that a continuous or semi-continuous stream of acid is mixed with a continuous or semi-continuous stream of aqueous waterglass solution.--

sub
B10

--63. (NEW) The method for the production of organically modified aerogel according to claim 62, characterized in that the acid stream is admixed with the aqueous waterglass solution through a mixing nozzle.--

--64. (NEW) The method for the production of organically modified aerogel according to claim 54, wherein step b) results in a hydrophobic gel in a liquid phase substantially immiscible with water, which liquid is separated from an aqueous-phase formed by the water from the hydrogel.--

--65. (NEW) The method for the production of organically modified aerogel according to claim 11, characterized in that the hydrophobizing-agent comprises at least TMCS and the liquid phase comprises at least HMDSO.--

--66. (NEW) The method for the production of organically modified aerogel according to claim 12, characterized in that at least a portion of the HMDSO is subsequently recycled.--